

不锈钢精轧管（不锈钢空心杆）



内径(mm) ID	外径(mm) OD	壁厚(mm) Thickness	重量(Kg) Weightness	外径公差 Outer Tolerance		标准长度(mm) Standard Length	电镀前表面光洁度 Before Chrome Plated Surface Roughness
				f7	f8		
13	18	2.5	0.98	-16/-34	-16/-43	2000	Ra ≤ 0.4
16	20	2	0.91	-16/-34	-16/-43	3000	Ra ≤ 0.4
20	25	2.5	1.42	-20/-41	-20/-53	3000	Ra ≤ 0.4
25	30	2.5	1.74	-20/-41	-20/-53	3450	Ra ≤ 0.4
32	38	3	2.65	-25/-50	-25/-64	3000	Ra ≤ 0.4
40	50	5	5.68	-25/-50	-25/-64	3000	Ra ≤ 0.4
50	60	5	6.94	-25/-50	-25/-64	3000	Ra ≤ 0.4
55	70	7.5	11.84	-30/-60	-30/-76	3000	Ra ≤ 0.4
80	100	10	22.73	-36/-71	-36/-90	3000	Ra ≤ 0.4
90	120	15	39.77	-36/-71	-36/-90	3000	Ra ≤ 0.4

备注：不锈钢精轧管外表可以电镀，通常电镀镀层厚度是15μm，电镀层也可以根据客户的要求选择相应的厚度。电镀后，外表面的光洁度 Ra ≤ 0.2
Note: Surface of Stainless Steel tube can be Chrome Plated, Usually the Chrome Plated layer thickness is 15μm, In addition, Chrome Layer Thickness can be selected by Customers. After the chrome plated, the surface roughness is Ra ≤ 0.2